

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

2349-103US

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.5)

09/786030

INTERNATIONAL APPLICATION NO.

PCT US99/23612

INTERNATIONAL FILING DATE

October 12, 1999

PRIORITY DATE CLAIMED

October 13, 1998

TITLE OF INVENTION

ELECTROSTATIC PRINTING OF FUNCTIONAL TONER MATERIALS FOR ELECTRONIC
MANUFACTURING APPLICATIONS

APPLICANT(S) FOR DO/EO/US

Robert H. Detig

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
- ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
- ☒ A copy of the International Search Report (PCT/ISA/210).
- ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
- ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
- ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
- ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
- ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☒ Certificate of Mailing by Express Mail
20. ☒ Other items or information:

Response to Written Opinion (4 pages)

Patent Application (38 pages)

Drawings (15 pages)

PCT Request (4 pages)

PCT Demand (3 pages)

Verified Statement Claiming Small Entity

Express Mail Certification No. EL640250087US

Postcard (1 page)

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.5) 097786030	INTERNATIONAL APPLICATION NO. PCT US99/23612	ATTORNEY'S DOCKET NUMBER 2349-103US
---	--	---

21. The following fees are submitted:				CALCULATIONS PTO USE ONLY	
BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :					
<input type="checkbox"/>	Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO	\$970.00			
<input type="checkbox"/>	International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO	\$840.00			
<input type="checkbox"/>	International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO	\$690.00			
<input checked="" type="checkbox"/>	International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4)	\$670.00			
<input type="checkbox"/>	International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4)	\$96.00			
ENTER APPROPRIATE BASIC FEE AMOUNT =			\$690.00		
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				\$0.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	22 - 20 =	2	x \$18.00	\$36.00	
Independent claims	5 - 3 =	2	x \$78.00	\$156.00	
Multiple Dependent Claims (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL OF ABOVE CALCULATIONS =				\$882.00	
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable). <input checked="" type="checkbox"/>				\$441.00	
SUBTOTAL =				\$441.00	
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)). <input type="checkbox"/> 20 <input type="checkbox"/> 30 +				\$0.00	
TOTAL NATIONAL FEE =				\$441.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL FEES ENCLOSED =				\$441.00	
				Amount to be: refunded	\$
				charged	\$

☒ A check in the amount of **\$441.00** to cover the above fees is enclosed.

☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees.
A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **23-3040** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Richard C. Woodbridge, Esq.
Woodbridge & Associates, Inc.
P.O. Box 592
Princeton, New Jersey 08542


SIGNATURE

Richard C. Woodbridge

NAME

26,423

REGISTRATION NUMBER

FEB. 28, 2001
DATE

**VERIFIED STATEMENT (DECLARATION) CLAIMING SMALL ENTITY
STATUS (37 CFR 1.9(f) AND 1.27 (c)) - SMALL BUSINESS CONCERN**

Docket No.
2349-103US

Serial No.

Filing Date
Herewith

Patent No.

Issue Date

Applicant/ **ROBERT H. DETIG**
Patentee:

Invention:

ELECTROSTATIC PRINTING OF FUNCTIONAL MATERIALS FOR ELECTRONIC MANUFACTURING

I hereby declare that I am:

- ☐ the owner of the small business concern identified below:
☒ an official of the small business concern empowered to act on behalf of the concern identified below:

NAME OF CONCERN: Electrox CorporationADDRESS OF CONCERN: 185 Union Avenue, New Providence, New Jersey 07974

I hereby declare that the above-identified small business concern qualifies as a small business concern as defined in 37 CFR 121.3-18, and reproduced in 37 CFR 1.9(d), for purposes of paying reduced fees under Section 41(a) and (b) of Title 35, United States Code, in that the number of employees of the concern, including those of its affiliates, does not exceed 500 persons. For purposes of this statement, (1) the number of employees of the business concern is the average over the previous fiscal year of the concern of the persons employed on a full-time, part-time or temporary basis during each of the pay periods of the fiscal year, and (2) concerns are affiliates of each other when either, directly or indirectly, one concern controls or has the power to control the other, or a third party or parties controls or has the power to control both.

I hereby declare that rights under contract or law have been conveyed to and remain with the small business concern identified above with regard to the above identified invention described in:

- ☒ the specification filed herewith with title as listed above.
☐ the application identified above.
☐ the patent identified above.

If the rights held by the above-identified small business concern are not exclusive, each individual, concern or organization having rights to the invention is listed on the next page and no rights to the invention are held by any person, other than the inventor, who could not qualify as an independent inventor under 37 CFR 1.9(c) or by any concern which would not qualify as a small business concern under 37 CFR 1.9(d) or a nonprofit organization under 37 CFR 1.9(e).

Each person, concern or organization to which I have assigned, granted, conveyed, or licensed or am under an obligation under contract or law to assign, grant, convey, or license any rights in the invention is listed below:

- ☒ no such person, concern or organization exists.
☐ each such person, concern or organization is listed below.

FULL NAME _____
 ADDRESS _____

☐ Individual ☐ Small Business Concern ☐ Nonprofit Organization

FULL NAME _____
 ADDRESS _____

☐ Individual ☐ Small Business Concern ☐ Nonprofit Organization

FULL NAME _____
 ADDRESS _____

☐ Individual ☐ Small Business Concern ☐ Nonprofit Organization

FULL NAME _____
 ADDRESS _____

☐ Individual ☐ Small Business Concern ☐ Nonprofit Organization

Separate verified statements are required from each named person, concern or organization having rights to the invention averring to their status as small entities. (37 CFR 1.27)

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.28(b))

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application, any patent issuing thereon, or any patent to which this verified statement is directed.

NAME OF PERSON SIGNING: Robert H. Detig

TITLE OF PERSON SIGNING: President

OTHER THAN OWNER: _____

ADDRESS OF PERSON SIGNING: 185 Union Avenue, New Providence, New Jersey 07974

SIGNATURE: _____

DATE: 20.19.01

Rec'd PCT/PTO 28 FEB 2001

**TITLE: ELECTROSTATIC PRINTING OF FUNCTIONAL
TONER MATERIALS FOR ELECTRONIC
MANUFACTURING APPLICATIONS**

5

10

BACKGROUND OF THE INVENTION

1. Field of the Invention.

The invention concerns a process for the electrostatic printing of functional
15 materials configured as liquid toners on relatively thick glass plates for various
manufacturing applications.

2. Description of the related art.

Flat panel displays or wall type television sets have been discussed in the prior
art literature for about forty years, but few have been produced. As of mid 1998 there
20 were three primary flat panel technologies for flat panel displays:

- a. Field Emission Displays (FED's.)
- b. Plasma Displays
- c. Active Matrix Liquid Crystal Displays (AMLCD)

Field emission displays are a relatively new technology. They consist of an
25 array of field emission points in a vacuum, spraying electrons onto a phosphor screen.
With three color dots on the screen and addressability of the emitting points, one has a
full color display.

The Plasma displays have been produced for about 25 years, mostly as a single
color orange neon "glow discharge". In the last 10 years, UV light from this
30 discharge has been "harnessed" to excite three color phosphors to produce a color
plasma displays. 40" diagonal displays have been recently announced, but their cost
is about \$10,000.

Active matrix liquid crystal displays have been intensively developed for
production. Billions of dollars have been spent on their development over the last 20
35 years, but the results have been only an expensive small display (10.4 inch diagonal)

09786030.02301

for lap top computers. The 1996 cost of a 10.4" display is about \$500. Wall type TV units, 20" diagonal or so, are perhaps available after the year 2000, but very expensive.

The reason for the small size/high cost of production are the currently used manufacturing techniques. These include:

- a. photolithography or the patterning of photo sensitive resists and the "washing" and etching processes that are attendant to them.
- b. the silk screen printing of relatively large area features (30 μ or more)
- c. the low pressure sputtering processes for coating glasses with metals like aluminum or indium / tin oxide (ITO), a transparent electrode or dielectrics like SiO₂.

In all cases the process has many steps, many in which the glass has to be heated and then cooled back to room temperature before the next step. Each of these steps requires a large piece of capital equipment in a class 100 clean room whose capital cost is \$500 per square foot for the room itself. The capital equipment runs the gamut from a \$40,000 liquid etcher, or developer, to a \$2.5M stepper to a \$4M sputtering cluster (six to eight vacuum chambers that accept 1m x 1m glass).

There is "suite" of expensive capital equipment in a typical \$500 per square foot clean room so that the cost of a modern AMLCD production facility is approximately \$500 Million. None of the raw materials for the displays, including the glass, glass powder or frit, phosphor, aluminum or nickel, resin or color filter resins are very expensive. Costs are incurred by the capital equipment and low yield of a complex process with many steps.

What is needed is a simpler manufacturing process with fewer steps that requires less capital equipment, does not involve heating and cooling within the imaging step as this dimensionally distorts the glass substrate by thermal expansion, and is implementable with relatively inexpensive machinery, i.e. no vacuum chambers, laser exposure steps etc.

Electrostatic printing has been used for color proofing in Du Ponts EMP process during the late 1980's. Du Pont used the electrostatic printing which is described by Reisenfeld in US No. 4,732,831. It used liquid toners that were transferred directly to a smooth, coated sheet of paper.

The transfer of liquid toner, which is important to this invention, was disclosed by Bujese in US No. 4,879,184 and US No. 4,786,576. These documents teach the transfer of liquid toners across a finite mechanical gap, typically 50 μ to 150 μ . This technology has been applied where toner, with etch resist properties, was transferred to copper clad glass epoxy boards.

Other prior work related to the printing plate and "gap transfer" includes M.B. Culhane (Defensive Publication# T869004, Dec 16, 1969) and Ingersol and Beckmore to the electrostatic printing plate (US No. 3,286,025 and RE 29,357; RE 29,537 respectively).

SUMMARY OF THE INVENTION

Briefly described, the present invention teaches a technique for the electrostatic printing of functional materials on glass to produce various "microstructures" like ribs or electrodes, spacers, filters etc. by a copy machine type of device at rates from 0.1 to 1.0 m/sec. In some cases there is a later step of sintering or electroless plating, but this is "after the fact" in that dimensional accuracy was previously determined by the printing step done at room temperature. The functional materials include metals, dielectrics, phosphors, catalytic seed materials, etc. configured as liquid toners. Since the substrate material is glass it presents special requirements:

1. It is mechanically of irregular shape (i.e. it is wedge shaped in orthogonal directions and its thickness has considerable variation); and,
2. It is a very thick material to be electrostatically imaged compared to the paper or polymeric films printed on by copiers or laser printers.

For this reason the invention uses liquid toners (dispersions of solid particles; metal, glass, etc.) that can be electrostatically transferred across a significant mechanical fluid filled gap.

While the "gap transfer" technique just described is useful in production machinery handling 1.0m by 1.4m plates, there are many situations where the printing capability on a relieved surfaced is a significant advantage, and the magnitude of surface relief can be quite substantial, of the order of 0.1mm or 100 μ or more.

The electrostatic printing function is typically done in one process step. Afterwards the particulate mass is fused into a solid structure with a subsequent heating step. In one embodiment of the invention, catalytic seed toners are printed followed by "electroless" plating steps where metals like copper, or nickel, are deposited on the glass.

Finally, there are certain partially manufactured products like color filters or CRT face plates which can be used in a process wherein the final part plays the role of a printing plate to print on itself. This is very simple and therefore inexpensive process which contains a "self-healing" feature. Imperfections in the semi finished parts are automatically overprinted with the liquid toner.

The invention may be more fully understood by referring to the following drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

- Fig. 1 illustrates an overall mechanical schematic of the invention.
- Fig. 2 illustrates a detailed view of the nip between drum and glass.
- Figs. 3a-d illustrate the electrostatic printing plate and the four steps in the imaging process.
- Figs. 4a-c illustrate the progressive exposure of the electrostatic printing plate.
- Fig. 4d illustrates a plate exposed one quarter of its thickness.
- Figs. 5a-b illustrates the ideal and typical charge decay cures for the electrostatic printing plate.
- Figs. 6a-d illustrates the four typical corona devices used in copy machine and electrostatic printers.
- Figs. 7a-b illustrates the printing plate current versus voltage for smooth wire and pin array corona units respectively.
- Figs. 8a-b illustrates the printing plate current versus the voltage on the plate for dicorotrons and scorotons respectively.
- Fig. 9 illustrates the plate/glass layout with its equivalent circuit.
- Figs. 10a-b illustrate electrical changes induced in printing plate during the transfer step.
- Fig. 11 illustrates a mechanical schematic of a "flat" to "flat" printing apparatus.

Fig. 12 illustrates a cross-section of a typical AC plasma display panel.

Figs. 13a-c illustrate detailed sequences of manufacturing steps in the production of critical features of the AC plasma display.

Fig. 14a-c illustrates the "self-printing" of the black intermatrix of a color
5 filter panel

Fig. 14d illustrates the self-printing of a vacuum phosphor front panel.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

During the course of this description, like numbers will be used to identify like elements according to the different views which illustrate the invention.

10 Fig. 1 shows an overall mechanical schematic of the preferred embodiment. Drum 10 has a latent electrostatic image 13 on its surface 11. It is charged by sensitizing corona 12. If it is a photo sensitive surface it is exposed in an image wise fashion by LED/ strip lens assembly 14. Alternately it could compose an electrostatic printing plate as disclosed by Reisenfeld of US No. 4,732,831 where the image areas
15 retain charge and the background areas discharge before the drum 10 rotates to the developer unit 16. The unit 16 is comprised of toner developer roller 18 that are splashed with liquid toner by pipe 20. They rotate in such a manner as to move in the same direction of the drum but typically at a relative velocity of 1.5 times. Reverse roller 22 rotates in a manner opposite the drum 10 and with a relative velocity of 3
20 times. The purpose of this reverse roller 22 is to scavenge excess toner liquid off the image surface 11 which also controls unwanted background. A corona unit 24 at roughly the 5 o'clock position serves to "compact" the toner image before transfer. This is also referred to as "depress" corona.

Glass plate 26, which is pre-wetted with toner diluent, moves from right to
25 left. It rests on insulating rollers 28 which are spaced with respect to the drum surface 11 to provide a nominal gap 42 between the glass surface 26 and the drum surface 11. Means are used to "float" either the image drum 10 with respect to the glass surface 26 or the glass surface 26 with respect to the drum 10, or glass 26, these are well known to those skilled in the mechanical arts. Corona unit 30 charges the bottom
30 surfaces of the glass 26. Wire 31 is raised to about 7 kilovolts grounded mechanical shutters 32 are adjustable to charge the glass 26 at the proper desired location to achieve optimum toner transfer. Corona unit 34 is an AC corona discharge to

09786030-072801

discharge the drum 10 before cleaning. Alternately this unit, or a second AC corona, may be located after cleaning unit 36. This first AC corona is not shown.

Cleaning unit 36 typically consists of a squeegee roller 38 that does bulk, rough removal of residual toner, while wiper blade 40 does the final, complete
5 cleaning of the drum surface 11. The drum 10 is now ready for the next image.

Important details of this embodiment are revealed by Fig. 2. Here is shown an enlarged view of the drum 10, gap 42, glass structure 26 at the transfer point, nominally at 6 o'clock. The drum 10 is wet with liquid toner and residual diluent coming into the nip formed by drum 10 and glass 26. The glass is pre-wetted with
10 clear diluent to ensure that the gap between drum and glass is filled with liquid. Metering of liquid on the drum and the pre-wetting liquid on the glass is not very precise so a wave of excessive liquid 44 builds up in the input to the nip. This is referred to, herein, as the Tsunami effect. The toner on the drum before transfer 50
needs to transfer to the glass in a location of low turbulence, about 6 o'clock.

Alternately on the output end, the amount of liquid between drum and glass is
15 precisely determined by the gap which is between 50 μ to 150 μ and can be easily controlled to +/- 5 μ with the "floating" techniques mentioned previously. Therefore a "film splitting" occurred as shown in Figure 2 not necessarily 50%/50% as suggested by this drawing. Actual values will depend on the surface energy of the drum surface
20 (amorphous selenium or silicon or alternately a photopolymer) versus that of the glass. For the purposes of this invention the film splitting point 46 is precisely defined and unchanging for particular materials and one gap setting while the wave front 44 is highly unstable and moves to the right from the beginning of the glass sheet to its end and can become quite violent and turbulent.

25 Important features of the preferred embodiment are now evident:

First: the actual transfer electric fields can be quite large as typical soda lime glass has substantial electrical conductivity (as much as 10^{-10} mho/cm) so the corona charge migrates through the glass to near the transfer point. As the drum and glass surface start moving away for each other
30 very high electric fields can be generated.

Second: By moving the location of the corona and the shutters laterally, the exact location of the transfer "zone" can be moved with respect to the

wave 44 and exit film splitting point 46. US No. 4,849,784 by Blanchet-Fincher teaches the importance of not attempting gap transfer in the turbulence of the input wave.

Third: After transfer toner particles 48 are tightly bound to the surface of the glass by the internal transfer charges from the transfer corona. This prevents them from being smeared by random motion of residual diluent liquids on the glass before the toner is dried. Alternately if toner is transferred to a metal surface it is held to that surface by its "image" charge "seen" in the metal. This is classical electrostatic theory. Typically these "image" forces are significantly smaller than the strong binding forces between surface toner and the nearby transfer charges.

Other important features of this invention are the ability to print very large substrates, one meter by one meter or more with very small "features" (i.e. the dimensions of the image elements) and with very high levels of "overlay" accuracy (i.e. the registration of features) on one layer (or printing step) to overlay accurately the features on subsequent layers (or printing steps).

The electrostatic printing plate is shown in Fig. 3a is a photopolymer layer 52 bonded to an electrically grounded substrate 54. A photopolymer layer 54 is heat and pressure laminated to a grounded substrate, typically an aluminized polyester film (PET). It is then exposed through a contact photo tool to actinic radiation (350nm to 440nm wavelength) to cross link the exposed areas. In Fig. 3b the plate is charged by a corona unit 56. The cross linked areas are much higher in electrical resistivity than normal photopolymer so they store charge for significant periods of time. After a suitable delay to allow the normal photopolymer to discharge, we have a latent image on the printing plate as in Fig. 3c. In Fig. 3d a "reversal" development is effected with a liquid toner 58, i.e. development of the discharged areas of the plate (those referred to as normal photopolymer or not cross linked). Note the process can be a "normal" image, where the charged areas are developed or reversed as previously mentioned.

The Electrostatic Printing Plate can be film coated from a liquid solution which can be dried and partially hardened by a gentle bake. Coating methods include

roller coating, spray coating, spin coating, dip coating or meniscus coating. Useful liquid photopolymers are usually negatively acting ones, those that cross link and that are insoluble in hydrocarbons or at least not significantly swelled by them. Typical examples of commercially available liquid materials are: Hoechst AZ-5200 IR, and
 5 MacDermid HDI-1, 2 or 3, also Mac Dermid. MT-1400. The dry film photopolymers are precast films than can be heat and pressure laminated to suitable substrates. They include these materials:

	DynaChem [®]	AX 1.0 or 1.5
		UF 0.5 or 1.0
10		5032, 5038, 5050
	MacDermid [®]	SF- 206
		CF-1.3
	DuPont Riston [®]	9512
		4615

15 The liquid resists can range in thickness from a fraction of a micron to about 15 μ to 20 μ depending on the coating technique used. They are typically in the fractional to 15 μ range. The dry film resists tend to be much thicker in the 13 μ to 50 μ range; the ones of greatest interest here are 25 μ to 38 μ thick. But one requirement in flat panel manufacture is the generation of ever smaller features, in the 10 μ to 5 μ
 20 range. This presents some difficulty with resists in the 30 μ to 50 μ range; in the 30 μ to 50 μ range; less of a problem in the 5 μ to 10 μ range.

An important feature of this invention is the partial exposure of the photo resist. Data has shown that the photopolymer 52 is exposed in ever increasing thickness of a layer starting at its surface, as shown in Fig. 4a through 4c.
 25 Increasingly by longer exposure to actinic radiation 60 cross-links ever deeper layer of the photo polymer. Therefore if one is using photopolymer at 38 micron thick but wants to make 5 μ features, one might expose only one quarter of it in thickness as shown in Fig. 4b. One now has highly resistive image in a "sea" of less resistive background areas. Since we never remove the unexposed background areas (an
 30 indeed their presence is a critical element in the success of the process, as discussed next), the partially exposed (or unexposed layers under the image) present no

problems. One determines the proper level of exposure for the "partial exposure" condition by a series of increasing exposure levels and measuring the charge voltage in large solid areas.

A second important feature of this invention is the need to keep the initial charge voltage on the exposed and unexposed regions to be either equal or within 50% of each other (i.e. $V_{\text{unexposed}} = 0.5 V_{\text{exposed}}$). The reasons for this are subtle, but crucial, for the success of the process. Fig. 5a shows the ideal charge decay curves for the image elements 66 ($V_{\text{exposed}} = f(t)$) and the background regions 68. ($V_{\text{unexposed}} = f(t)$). Note after a short period of time there is no voltage in the background regions while the voltage and the image elements has decayed very little. While this is ideal and theoretically achievable in practice the initial charge voltage in the unexposed regions of the plate should be 50% or more of those values for the exposed regions as shown in Fig. 5b, exposed 70 and unexposed 72. The reason for this is a phenomenon called the "island effect". Basically a small spot of a good dielectric like PET setting on a "sea" of bare copper cannot be charged to any significant value because of the electric field lines from the "island" to its surrounding "sea" which is at zero or grounded potential. These "field lines" direct incoming electric charge away from the image element and they land on the background areas.

Some photopolymers in the unexposed condition turn out to be "too" conductive and will not charge up to any significant value under the corona charge. Such plates when imaged by simple conditions will develop out the large image features but small image detail or fine structures are lost.

Such photopolymers can be used if one gives them a broad pre-exposed of the unexposed plate to bring it up to the proper electrical resistivity so that the initial voltage in the background areas is adequate. Then the pre-exposed plate is imaged with a photo-tool to produce a proper image above the pre-exposed level. This has been done is silver halide for years and is called "pre-fogging" of the plate. Pre-exposure of an electrostatic printing plate is discussed in prior art literature such as Bujese in US No. 4,968,570.

Other photopolymers have just the proper level of resistivity in the unexposed regions and require no pre-exposure or "pre-fogging". Some materials easily pick up moisture from the air and their intrinsic or unexposed resistivity depends upon their

storage history and packaging. Generally these effects are not troublesome once known by the user and proper modern packaging and careful storage can yield a well defined photopolymer plate. Bench mark testing of each batch of photopolymer will easily yield data to define proper exposure and "pre-fog" exposure if needed.

5 A third aspect of an optimized electrostatic printing process is the design and "type" of corona unit use as the charge corona. The machine design shown in the invention includes an AC erase discharge corona located just in front of the charge or sensitizing corona. By careful attention to design the AC corona will "reset" or discharge all areas of the plate after the last print cycle. Now the plate is ready to be charged. Ideally the charging corona will charge all areas of the plate to the same voltage whether they be large solid areas of image, large areas of background (the unexposed regions) and the fine image structure.

There are basically four different structures used to make corona units in copiers and printers:

- 15 1. The familiar bare wire in a metallic shroud.
2. The unit "a" with an electrically biased metal screen or grid between it and the plate or drum (the Xerox trademark for this is a scorotron).
3. The glass coated wire driven by an AC signal in a "U" shaped shroud that has a DC bias, the dicorotron.
- 20 4. An etched metal "saw tooth" structure of corona emitting points.

The above approaches have different voltage versus corona current densities that will show which one is optimum for this situation. The electrostatic printing plate poses new problems for corona design. The plate has areas of two different electrical resistivities, the high resistivity charge retaining layer and the lower resistivity background regions. It has already been discussed how a plate could be pre-fogged to raise the background area resistivity to a point where its charge voltage would decay to a negligible value (typically 10% of the initial voltage) within the process time between charging and development. Given that this has been accomplished, the initial charge voltage in the non-exposed or background areas are a fraction of the initial voltage in the exposed areas can be maximized by the choice of charge corona type and its design details. Procedures to accomplish this will now be described.

The various corona devices in use are shown in Fig. 6. The top figure shows the oldest design dating to the late 1950's, the corona unit 74 or a bare wire usually gold plated tungsten of 50μ to 75μ in diameter in a grounded metal shroud. In some designs the front aperture was constricted inward to serve as a self extinguishing function in that the surface to be charged would not exceed a certain value. This was important otherwise the drum voltage, if excessive, could puncture the photo conductive surface of the drums used at that time, causing permanent damage.

An earlier version of the "pinched" design was the scorotron at the bottom of Fig. 6d. Here a metallic grid 76 structure in front of the corona wire is biased to a voltage perhaps 10% to 25% above the desired surface voltage (typically +800 for a 60μ thick amorphous selenium layer).

The cost of the 1000 volt power supply to bias the grid structure and the assembly costs of the scorotron versus the corotron were the reason for the design of the "pinched-in" Corotron of Fig. 6a.

One problem with the simple corona unit is that in the negative mode the corona discharge is not positionally stable but moves back and forth randomly. One "fix" for this is to super-impress on the DC voltage to the corona wire, typically a ripple value of 10% to 20% of the DC. This caused the high intensity nodes of negative corona discharge to move down the wire at the AC frequency (usually 50 or 60 Hz). This simple, low cost solution was adequate for low speed copiers or printers, but when higher speed units were being designed, a new corona structure, the dicorotron 18 was invented, see Fig. 6c. This used a glass coated wire which was driven by an ac voltage. The shroud (or shield) was biased to a DC voltage which would define whether positive or negative charge was extracted by the corona unit. This design has the advantages of a large diameter glass coated wires that was not easily "fouled" with random dust or toner particles. The bias power supply for the shield was also a low cost design. One unfortunate aspect of this design was that the dicorotron corona unit produced considerable levels of ozone. This trace gas is becoming unacceptable in the office environment.

That situation led to the design of the "pin corotron" 80 or a saw tooth edge 82 that is driven to a high voltage. With a properly made "saw tooth" the corona unit produced very uniform corona discharges, especially negative discharges. This

corona unit has been highly successful in recent Xerox® organic photoreceptor machines. The important performance characteristics of a corona unit is the current to the plate to be charged versus the voltage to which the plate has charged. Figs. 7 and 8 show these curves. Note that the wire and pin corotron have the same V-i curves
5 Fig. 7a but that the AC curve Fig. 7b is quite different from the DC curve.

This invention uses an ac neutralizing corona unit to discharge the printing plate at the end of the printing cycle. Either the bare wire or pin corona are adequate for this job. The charging corona is located just after the neutralizing corona. Here a V-i curve is desired that will best charge the exposed and unexposed regions of the
10 printing plate to the same voltage.

The ideal voltage- current characteristic from the corona unit would be one in which the corona current density (in microamps/cm²) would be independent of printing plate voltage, or a flat straight line in Fig. 7 and 8. Then if the plate is charged quickly, both exposed and unexposed plate areas would charge to the same
15 value, after a suitable delay the unexposed regions would decay to a negligible value yielding an excellent electrostatic "contrast" (the difference between image and background).

Therefore, the best corotron design for this invention is the DC bare wire or pin corotron whose V-i curve is shown on Fig. 7a. It's V-i curves are the "flattest" of
20 the four types of corona units and will yield the high ratio of unexposed to exposed initial charge voltage.

DETAILS OF THE TRANSFER PROCESS

An important part of the invention relates to details of the transfer process not usually encountered in typical transfer processes to film and paper in the copying and
25 laser printing industries. There toner, either liquid or dry is transferred to relatively thin webs of paper or polymeric film, typically 75 to 100 micron and in all cases the web is in virtual contact with the image surface.

In the invention toner images are transferred to relatively thick layer of glass, 0.5 to 3.0 mm thick (500 to 3,000 micron) spaced away from the image by a fluid
30 filled mechanical gap of 50 to 150 microns. Relative conductivities of the glass versus the gap filling liquid (toner plus added diluent), capacitances, applied voltages and the time over which they are applied etc. are important.

Figure 9 shows a mechanical schematic of the transfer process and a electrical equivalent circuit which allows one to calculate the voltage division across the three elements (glass, gap, and printing plate) during the transfer process.

A. Electrical conductivity of the glass versus the conductivity of the gap liquid

5 The most critical issues are the conductivities of the liquids in the gap versus the glass as this determines the voltage division between glass and gap. If most of the voltage appears across the glass and very little across the gap between plate and glass, all of toner will transfer. This is best illustrated by some examples:

Printing plate 400 consists of a photopolymer 402 of 10 to 50 micron
10 thickness connected to electrical ground. Receiving glass plate 404 of typical thickness 0.5 to 3.0 mm thickness is backed by a field electrode 406 connected to transfer voltage 408. It is separated by mechanical gap 430 from printing plate 400. The equivalent circuit for this structure 412 is shown to the right.

A-1. A Glass of Interest is Electroviere ELC- 7401 made in Switzerland.

15 If charged and then the voltage decay measured it shows a decay time constant of 1 second which calculates to a resistivity of $2 \times 10^{+12}$ ohm • cm. Typical ranges of toner bath conductivities are of the order 10 to 100 pico mho/cm (10^{+11} to 10^{+10} Ω • cm resistivity). There is one caveat to be disclosed. The charging test with the glass is a dc test and measures the flow of electronic charges through the glass, while the
20 measure of toner conductivity is an 18 hertz test that measures back and forth flow of electrons, ions, and charged toner particles.

Now applying electromagnetic theory to the glass 404/gap 430 structure initially when a step function of voltage is applied the voltages divide capacities between the elements, glass, gap, and plate. Since the imaged areas of the plate 400
25 are highly resistive they can be disregarded for short periods of time. Since the glass is thicker than the gap, typically 10 to 100 times, and it's dielectric constant is 5 verses 2.1 of the liquids in the gap, the voltages divided preferentially across the glass with little across the gap. If the conductivity of the gap fluids is higher than the glass this situation will worsen the time and transfer will be inhibited.

30 With time, the voltages divide resistively between glass and gap. If the conductivity of the gap fluids is higher than that of the glass, practically all of the voltage is across the glass and none across the gap. If toner had transferred, it will

T 08220 02098760

back transfer due to the image charges on the printing plate. This, in fact has been observed.

A-2 Conductivity of the Diluent Used to Fill the Gap

Typically when a printing plate is imaged excess toner fluids are very effectively removed by a "reverse roller" that scavenges liquid containing random background particles; the result being a almost dry plate. Now the plate and glass are placed in proximity with each other and the gap between them filled with fluid. If one fills the gap with clear Isopar (conductivity less than 0.15 pmho/cm) the toner charge may be reduced by the lack of charge director is the clear Isopar. If one fills the gap with Isopar plus charge director with a conductivity of 20 pico mho/cm, the voltage division between glass and gap suffers. Again the demands of maintaining charge on the toner particles versus the conductivity of the gap fluids conflict. Conductive Isopar in the gap is desired but may not be possible if the glass has very high electrical resistivity.

Printing plates 430 and 432 in Figs. 10a and b respectively are "negative" images of each other. 430 is cross linked in the image area and developed with toner 434. 432 is cross - linked in the non-image areas and developed with toner 434. Both plates are sensitized with charges 433. Field plates 436 and driven by voltages 438 and 440 respectively. Receiving glass 442 accepts the transferred image. Mechanical gap 444 is filled with transfer fluid (not shown). High resistivity regions 446 are the cross - linked regions of the plate. Induced charges 448 occur when the transfer voltage is applied and are restricted to the non-cross linked regions of the plate.

B. Mounting Techniques for the Printing Plate and Glass

To preserve the fidelity of the toner image on the plate the transfer electric field must be everywhere normal to the plane of the plate and undistorted on the edges. And since we are transferring to glass with a resistivity of the order of 10^{+12} to 10^{+16} ohm • cm the mounting and holding of the plate must be consistent with these resistivities, i.e. these fixtures must be of materials substantially higher in resistivity. Even with the most conductive glass (lowest resistivity of 10^{+12} ohm • cm) some typical engineering materials, like cotton filled phenolics or poly acetals (Delrin of DuPont) may not be adequate for the job. For instance, Corning 7059 or 1737 glass is typically used for liquid crystal display panels for lap top computers. They have a

resistivity of the order of 10^{+16} ohm • cm. A cotton filled phenolic resin material would not be adequate. Teflon™ type materials with resistivities of 10^{+18} are needed.

Also the conductivity of the bath can cause problems around the edges of the printing plate. Since the substrate of the plate is electrical ground, the conductive gap filling liquids might distort the electric fields near the edges of the glass/ plate assembly if they can contact electrical ground causing distorted image transfer.

C. Induced Charges in the Printing Plate During Image Transfer

An important feature of using the fixed resistivity configuration electrostatic printing plate is a phenomenon that helps to "focus" or direct the toner particles during transfer IF the plate is used in the normal imaging mode. By this it is meant that the toner development of the charged areas of the plate as opposed to the "reversal" mode where the discharged areas of the plate are developed with toner particles. The former is used in a typical office copier while the latter is used in a laser or LED printer.

Refer to Figures 10a and b. Figure 10a shows the normal imaging mode, positive sensitizing charges developed with negative toner particles and transferred with a positive electric field. Figure 10b shows reversal with again positive sensitizing charges, positive toner particles transferred with a negative electric field. Note the charge retaining areas of the printing plate, they are highly resistive necessarily to retain the sensitizing charges. The other areas of the plate (areas not cross-linked in the plate exposure step) are much lower in resistivity.

During the transfer step, the transfer field "induces" electrical charges in these lower resistivity areas of the plate, which produces a significant result. Note the charge configuration in the "normal mode" plate, Figure 10a. The sensitizing charges are positive while the induced background area charges are negative. These background area negative charges enhance the strength of the imaging fields and help to control the direction of the toner particles during the transfer step. In the "reversal plate" (Figure 10b), charges induced in the lower resistivity regions of the plate (the non-cross-linked regions) are of the same polarity as the imaging fields and tend to reduce the fields. Indeed if the induced charge density equals that of the sensitizing charges there is no longer an imaging field and toner particles are free to move laterally during the transfer step. This will cause significant "de-focusing" of the

transferred toner image. For this reason, normal imaging is preferred when using the electrostatic printing plate for highest resolution images.

In summary, electrostatic printing process for printing functional materials on glass plates is a simple one with few process step. It has these advantages over

5 current technologies:

1. It is a simple, direct process that proceeds at high rates, to 1 meter/sec.
2. It deposits a wide range of functional materials (conductors, insulators, phosphors, catalyst, etc.) to high definition or resolution with precise positional accuracy (called "overlay" accuracy in the silicon chip
- 10 industry).
3. It prints on the glass surface without contact which has these advantages:
 - a. mechanical tolerances are loosened in the design of production machinery
 - 15 b. previously printed materials are not disturbed
 - c. it can print on a relief surface. In fact the invention can print a conductive line at the bottom of a 100 μ deep trench.
 - d. the invention can coat the bottom and walls of the trench with a phosphor material or other applications not yet defined.
- 20 4. This is no photolithographic patterning of the glass.
5. There is no mechanical handling of the glass from step to step. We load a clean sheet of glass into the printing device and out comes a finished plate ready for sintering.
6. The process is a room temperature process until sintering so critical to
- 25 large geometrics due to thermal glass. In the printing of color filters, the four filter colors are printed at room temperature, then baked at once.
7. Expensive functional material is not wasted.

First Alternate Embodiment of the Invention

30 Fig. 11 shows this embodiment. Chuck 100 carrying electrostatic printing plate 102 is transported on linear bearings 104 by belt drive 106, canted at roughly a 45° angle to the horizontal. At the beginning of the print cycle chuck 100 starts at the

top near pulley 108. Moving at uniform speed it passes corona unit 110 which charges the printing plate, 102 with a uniform electrostatic charge. After a short period of time, the low resistivity areas of the plate with discharge to a negligible charge level; the high resistivity areas of the plate retain the charge to near original levels.

This latent electrostatic image is now developed by liquid toner which floods the gap between developer roll 112 and plate 102. Valve 114 floods this gap with a measured quantity of liquid toner 116. Developer roll 112 has an electrical bias voltage 118 which controls the accumulation of unwanted toner particles in background areas of the image. After passing between the developer roll plate 102 is stripped of excess liquids by reverse roll 120. After this the liquid toner is compacted by "depress" corona 122. The image is now finally developed and ready for transfer to the receiving substrate.

Receiving substrate 130 rests on its chuck 132 which rides on linear drive 134 driven by belts 136 and pulleys 138. It moves right past valve 140 which wets it with a thin layer of clear Isopar diluent. It moves to transfer position 142 and stops. Chuck 100 carrying printing plate 102 rotates approximately 135° counter clock wise to a position in obverse relation to receiving substrate 130. Spacing means not shown, accurately position plate 102 from receiving substrate 130 by a precisely controlled mechanical gap, typically of the order of 50μ to 150μ. A voltage is applied to chuck 132 to create a transfer electric field which transfers the toner image on plate 102 to receiving substrate 130.

Chuck 100 with printing plate 102 is now lifted vertically by means not shown or simply rotated clock wise by approximately 135° to its original position. Receiving substrate 130 is now dried before removing it from its chuck 132. Plate 102 is now moved up the 45° ramp and cleaned by suitable means, not shown, to repeat the next printing step.

The manifestation of the invention has advantages over the rotating process of the preferred embodiment in that is a asynchronous, i.e. variable time intervals can be introduced between each step of the process; and transfer occurs in the flat to flat situation when hydrodynamic events and forces have subsided. Furthermore, the flat receiving substrate, which may be of the order 1m x 1.2m must be on the bottom so it

can be flooded by the diluent to fill the gap between the plate 102 and receiving substrate 130. Finally, the "overlay" accuracy of one flat plate, the printing plate; to a receiving sheet is much better, flat to flat, then in the dynamic situation of a moving flat sheet that needs to be accurately "phased" to a rotating print drum. Achieving very uniform linear and rotary drives are not trivial but phasing them "on the fly" to levels of their individual variations is a major task, all of which does not apply here.

Second Alternate Embodiment

Fig. 12 shows a cross section of the cathode plate 200 of an AC Plasma Color Display Panel. It consists of a glass back plate 200 with black glass spacer ribs 202 that optically and electrically isolated image cells from one another. These ribs are typically 100 μ high and 30 μ to 40 μ in nominal width. At the bottom of the "wells" are the address electrode lines of copper 204 or nickel metal. Covering the walls and bottom of the "canyons" is the phosphor 206 that converts the UV radiation from the plasma discharge to visible radiation, RG&B in the case of a color display. Alternate canyons are coated with red, then green then blue phosphor.

One advantage of the electrostatic printing technique is the non-contact or gap transfer aspect of it; i.e. the ability to transfer functional materials across relatively large mechanical gaps.

Fig. 13 is a greatly magnified picture of the mechanical gap 220 between the print drum and glass surface 200 of the invention. The gap here is set to a value of 150 μ . In the first manufacturing step glass toner is printed to make the spacer/isolator ribs 202. Four layers of toner 203 is shown, each about 25 μ high, one printed on top of the other. The manufacturing sequence is as follows:

- | | |
|--------|---|
| Step 1 | Print first layer of glass ribs |
| Step 2 | Dry the toner by blowing warm air on it to partially set the resinous material that coats the glass particles. Note it is desired to maintain this as a constant temperature process so warm air is needed to compensate for the natural cooling that occurs with the evaporation of the diluent liquid |
| Step 3 | Reprint and dry the second layer of glass toner |
| Step 4 | Reprint and dry subsequent layers of glass toner until the desired height is achieved. |

- Step 5 Fire the glass panel at high temperature to burn off the resin in
 the toner and reflow the glass particles to make a solid rib
- Step 6 The rib manufacture process is now complete.

Figure 13 shows the process for the printing of the metallic address electrodes
5 204 in the base of the canyons formed by the ribs. A palladium catalytic toner 224 is
image on the drum and transferred across the 150 μ gap to the base of the canyons.
The toner is dried leaving a very thin layer of palladium seeds in a line that runs the
length of the canyons. The plate is removed from the printing machine of the
invention and immersed in an "electroless" plating bath. Metal grows from solution is
10 on the palladium seeds, then on previously plated metal. Electroless processes have
advanced to a point where one can plate up to one micron of metal per minute. After
the growth of about 25 μ of metal 226, usually nickel, the cathode electrodes are
complete.

Figure 13 shows the deposition of phosphor toner 230 in the canyons.
15 Phosphor toner 230 is imaged on the plate and transferred across the 150 μ gap.
Generally the transferred toner moves in straight lines but can coat relief images like
coins. The toner image is sized to cover the walls of the canyons as well as the base
where the electrodes are located. Note one phosphor color is imaged at a time so the
printing plate has an image of every third canyon on it. After the first phosphor color
20 230 is imaged the toner is dried with warm air to set it; then the second color is
imaged; then the third color. The same printing plate can be used for all three colors;
all that is needed is to mechanically index the glass with respect to the printing drum.

The plasma display cathode plate is now finished. Glass ribs were built in 4 or
5 printing steps followed by a firing step to reflow the glass particles. Then electrodes
25 were printed with a catalytic toner followed by an electroless plating step. Finally
three color phosphors were printed in the canyons formed by the glass ribs.

Third Alternative Embodiment

An alternate method to produce conductors is to print metal toners themselves,
to burn off the resin that coats the metal particles; then reflow the metal into a smooth
30 conductor pattern. Using the invention of the preferred embodiment one prints an
aluminum toner onto the glass. The toner is then dried to temporarily fix it for
reasons of safe handling. Now a rapid thermal processing of the metal is effected,

where the toner and glass is raised to a temperature of 50° to 100°C below the softening point of the glass (approximately 500°C for soda lime glass). This effectively burns off the resin that coats the metallic particles. Now with an intense UV light source, the aluminum is heated to its melting point while the glass absorbs
5 little UV energy. Aluminum which melts at 659°C is a good choice of materials to be used with soda lime glass. Note this is not done in air but in a “reducing” atmosphere like one used in aluminum welding work.

Fourth Alternate Embodiment

In this embodiment the glass 300 in Fig. 14a is first coated with a thin,
10 transparent layer 301 that is electrically conductive. This very thin layer is not shown. Indium Tin Oxide (ITO) is a possibility except it absorbs about 5 to 10% of the transmitted light and ITO processing is expensive, of the order of \$5 per square foot. The ITO conductivity of 50 to 100 ohms per square for a typical 2μ thick layer is higher than needed for this electrostatic process. A conducting polymer as resistive as
15 10⁺⁵ ohms per square is adequate for this electrostatic process, all that is needed is to establish an electrostatic ground plane 302 as shown in Fig. 14a.

In this case the coated glass 300 is imaged with the RGB color mosaics 304 which are then reflowed by final heating. The plate is now complete except for the black intermatrix which has yet to be produced. Transparent conductive layer is
20 electrically grounded through edge contact 306 as shown in Fig. 14a. Now the entire plate is corona charged with a suitable corona generator 308 as in Fig. 14a. The conductive under layer discharges immediately, while the color mosaics retain their charge 310 for considerable periods of time, as much as thousands of a second depending on the resins used in the mosaics. The partially finished color filter plate is
25 now its own electrostatic printing plate, as seen in Fig. 14b. It can be developed in the reversal mode (i.e. develop the discharged [or uncharged] areas of the image) as is done in virtually all desk top laser printers.

In the example shown, the mosaics are charged positively so a toner with a positive charge 312 will develop the non-charged areas as in Fig. 14c. This black
30 toner will produce the intermatrix between the mosaics. After the toner is dried, it may be reflowed by heating if necessary, but there are good reasons to leave it a particulate layer which will hold the unfused toner in place.

One of the principal advantages of this embodiment is that the final printing operation of the black intermatrix is self-correcting of "self-healing". Any image defects in the mosaics will be over printed with black toner automatically. Also one does not need a high definition printing plate for the black intermatrix which must then be aligned to micron tolerances so as not to leave gaps between matrix and mosaic through which stray light will be passed. This self-correction feature is one of the greatest advantages of this embodiment.

Another "self-printing" example as shown in this embodiment is seen in Fig. 14d. This glass plate #330 is typical of the face plate of a field emission display (FED). The glass is first coated with black chrome oxide #332 to enhance optical contrast and with a metallic chrome layer #334 to conduct away to ground the electrons that hit the phosphor. It is desired to coat phosphor in the bare spaces on the glass surface between the chrome fingers which are all connected together. To "self-print" the phosphor toner the glass panel is placed on an electrically ground plate #336, chrome side up. Using a wire or metallic probe #338 the chrome layer is made to act as an electrode by connecting it to a high voltage power supply, as high as possible before electrical breakdown occurs. Liquid toner is now poured over the plate and it is noted that toner #340 "develops" on the bare glass areas by means of the fringing electrical fields. If the toner particles have a positive charge on them, a positive voltage must be connected to the chrome layer; with negative toner conversely a negative voltage with respect to ground is needed. As before open area defects in the chrome layer will have toner deposited on them in a "self-healing" manner.

Example 1 of the Preferred Embodiment

An electrostatic printing plate was made by laminating DynaChem 5038, product of DynaChem Inc., Tustin California, photopolymer dry film resist material to 0.003 inches thick black anodized aluminum foil from Lawrence and Frederick of Des Plaines, Illinois (the part number is 1145-003-1419-SB). The laminating was done on an industry standard dry film laminator made by Western Magnum. After cooling from the lamination process, the plate was exposed by a negative photo tool to nominal exposure level 100 milli joules/cm².

The plate was charged to a nominal image voltage of -800V by a corona discharge unit. After about 2 seconds it was developed with a glass particle liquid toner by merely pouring the toner over it. Clear diluent (typically Isopar G®, Exxon Corp.) was used to wash away background particles. 125μ thick spacers were placed on the plate edges and a glass plate wetted with diluent was placed over the spacers. Care was taken to ensure that no air bubbles were trapped in the space between the printing plate and the glass plate. The same corona unit was used to charge the top side of the glass plate with negative corona charges. The glass plate was lifted and an excellent glass toner image was found on the bottom surface of the glass plate. The glass was standard window glass (soda lime float glass) 0.090 inches thick.

Example 2 of the Preferred Embodiment

The glass toner of example 1, was prepared by the "organosol" process as taught by Kosel in US# 3,900,412. An organosol resin was polymerize in Isopar H diluent following the methods of Kosel. The resin had a Tg of -1 °C and a core to shell ratio of 4. It was designated the nomenclature of JB8-1 (Aveka Inc., Woodbury, Mn.) The toner contents were as follows:

75 gm glass powder, Ferro Corporation, Cleveland, Ohio, #EG-2030-VEG

25 gm resin, JB8-1

2 gm ZrHexCem, OMG Americas, Cleveland, Ohio, Prod. Cd. 949

300 gms of Isopar L®, Exxon Corporation

It was processed for one hour in a Dispermat F105® vertical bead mill made by Byk-Gardner Incorporated of Germany. Processing was done at medium speed. The resulting toner had the following characteristic:

mean particle size	1.27μ
toner conductivity	9.9 pico mho/cm
particle mobility	$3.06 \times 10^{-6} \text{ m}^2/\text{v} \cdot \text{s}$
Z (or zeta) potential	14.7 millivolts

The glass particles have a true mass density of 5.2 while the Isopar L® has a density of 0.8 so the toner settles out substantially in 15 to 30 minutes. It can be successfully re-dispersed by moderately shaking of the toner containers by hand.

Example 3 of the Preferred Embodiment

Example #1 was repeated with the toner of example #2 but the toner was transferred to Cr coated glass. 75mm x 75mm x 1.2mm Corning 7059® glass were sputter coated with 100nm to 150nm of pure chrome. The resulting surface had a brilliant shine to it. The Cr surface on the glass was wetted with Isopar and this wetted glass placed on the PET on a developed printing plate. The Cr surface was connected to a lab supply producing -1600V. Good glass toner images were transferred on the Cr coated glass. The PET spacers were 125 μ thick.

Example 4 of the Preferred Embodiment

A catalytic toner was prepared with the following ingredients:

2 gm of Palladium powder, Aldrich Chemical # 32666-6

17 gm of organosol resin, JB-8-1

1 gm of ZrHexChem

100 gm of Isopar L

The mixture was dispersed in the vertical bead mill for 1.5 hours at 2,000 rpm.

The resulting toner had these measured characteristics:

mean particle size 0.333 μ

conductivity 169 p mho/cm

The toner was imaged using the plate of Example 1 and transferred to soda lime glass plates. These plates were dried then put into an electroless copper bath (typically Shippley CuPosit™ 328, Shippley Inc, Marlboro Massachusetts) for 10 minute at 23°C. Significant copper metal was visible on the glass surface.

Example 5 of the Preferred Embodiment

An aluminum powder toner was prepared by the following formulas:

75 gm of Alex Al, Argonide Corp.

25 gm of organosol resin JB-8-1

2 gm of ZrHexChem

350 gm Isopar L

The mixture was dispersed for 1.5 hours in the vertical bead mill and the

resulting toner specifications were:

mean particle size 30 μ

mobility 6.95 x 10⁻¹¹ m²/v•s

conductivity 40 p mho/cm

zeta potential 5,314 m volts

The toner was imaged on the plate of example 1 and transferred to the same type to soda lime glass. After drying it was subjected to rapid thermal processing in the model CP-3545 RTP machine of Intevac of Rocklin, California. The toner and glass were pre-heated to 550°C in a non-oxidizing atmosphere. It was then exposed to intense UV radiation that heated the aluminum toner but not the glass.

Example 1 of the Fourth Alternate Embodiment

A 1.1mm thick plate of soda lime glass was patterned with black chrome oxide, then metallic chrome with phosphor openings of 60μ by 130μ in a solid pattern of 75mm x 100mm. The plate was placed, chrome side up on a grounded copper plate. Electrical contact was made with the chrome surface and the power supply was turned on to +6,000 volts. No break down occurred. The chrome surface was flooded with the phosphor containing toner. Similar to Example #2, the difference was equal amounts of phosphor and resin, 50g of phosphor, 50g of JB8-1. Unwanted background was washed away with clear Isopar G. The plate was allowed to air dry at room temperature. Good phosphor toner images were noted in the clear spaces between the chrome fingers. The phosphor toner NP-1053A was obtained from Nichia Kagaku Kogyo, K.K., Tokushima-ken, Japan.

Example 1 of the First Alternate Embodiment

A printing plate from 38 micron thick DynaChem 5038 photopolymer was charged and imaged with Indigo E-1000 toner with a concentration of 1.5% by weight and a conductivity of 25 pico mhos/cm. Corning 7059 glass 1mm thick was placed on PET film, 25 microns thick spacers, above the plate. The gap between glass and plate was filled with pure Isopar G whose conductivity is less than 0.15 pico mho/cm. An electrode was placed on top of the 7059 glass and excited to +10kv with respect to the grounded base of the printing plate. The transfer voltage was held for 10 minutes.

The glass was removed with the transfer voltage still applied and it was noted that no toner transferred. This shows that virtually all of the voltage appeared across the glass and none or little across the gap so no toner transferred.

Initially toner may have transferred to the glass due to the capacitive division of voltages between glass and gap (theoretically about 12% of the 10kv or 1200 v), but as the voltage across the gap collapses, the toner would back transfer to the plate.

Example 2 of the First Alternate Embodiment

5 The plate of Example 1 of the First Alternate Embodiment was imaged and developed. Electroveere glass ELC-7401 with a resistivity of $2 \times 10^{+12}$ ohm • cm was placed on 50 micron thick PET spacers. The gap between glass and plate filled with Isopar G spiked with Indigo Imaging Agent to a conductivity of 12.4 pico mho/cm. A transfer voltage of 4kv was applied to the top of the Electroveere glass for 5 seconds
10 while linearly reducing it to 3kv. The glass was removed with the 3kv transfer voltage still applied.

An excellent image was seen on the glass with very good edge acuity. The image was superior to a similar image created, using just clear Isopar G (i.e. very low conductivity) to fill the gap. Demonstrating that the charges, on the toner particles,
15 are better preserved with the conductive, gap filling liquid.

Example 3 of the First Alternate Embodiment

An image was created on the plate of Example 1 of the First Alternate Embodiment using that toner. 2.25mm thick soda lime float glass (i.e. common window glass) was placed on 50 micron PET spacers, above the plate. Isopar G
20 conductivity treated with Indigo Imaging Agent to a conductivity of 25 pico mho/cm was used to fill the gap between glass and plate. An electrode connected to 5kv of voltage was placed on top of the plate, which was reduced to 3kv in 5 seconds. The glass plate was lifted and an image of low density was found on the glass. A significant amount of toner remained untransferred on the printing plate. The
25 conductivity of the gap liquid reduced the effective voltage across the gap causing poor transfer.

If clear Isopar G is used good, complete transfer occurs though edge acuity may suffer. With this moderately resistive glass (of the order 10^{+13} ohm • cm), the conductive Isopar in the gap reduces the voltage across the gap resulting in
30 incomplete transfer.

In summary, this invention comprises a relatively uncomplicated high yield manufacturing process in which functional materials are configured as liquid

09786030-00280-1
T08220-00092750

electrographic toners that can be printed at commercially interesting rates of production in a non-contact mode. This non-contact feature allows one to print on non-flat surfaces or even relief surfaces such as ribbed surfaces.

While the invention has been described with reference to the preferred embodiments thereof it will be appreciated that various modifications can be made to the parts and methods that comprise the invention without departing from the spirit and scope thereof.

1997-1998		1998-1999		1999-2000		2000-2001		2001-2002		2002-2003		2003-2004		2004-2005		2005-2006		2006-2007		2007-2008		2008-2009		2009-2010		2010-2011		2011-2012		2012-2013		2013-2014		2014-2015		2015-2016		2016-2017		2017-2018		2018-2019		2019-2020		2020-2021		2021-2022		2022-2023		2023-2024		2024-2025		2025-2026		2026-2027		2027-2028		2028-2029		2029-2030		2030-2031		2031-2032		2032-2033		2033-2034		2034-2035		2035-2036		2036-2037		2037-2038		2038-2039		2039-2040		2040-2041		2041-2042		2042-2043		2043-2044		2044-2045		2045-2046		2046-2047		2047-2048		2048-2049		2049-2050		2050-2051		2051-2052		2052-2053		2053-2054		2054-2055		2055-2056		2056-2057		2057-2058		2058-2059		2059-2060		2060-2061		2061-2062		2062-2063		2063-2064		2064-2065		2065-2066		2066-2067		2067-2068		2068-2069		2069-2070		2070-2071		2071-2072		2072-2073		2073-2074		2074-2075		2075-2076		2076-2077		2077-2078		2078-2079		2079-2080		2080-2081		2081-2082		2082-2083		2083-2084		2084-2085		2085-2086		2086-2087		2087-2088		2088-2089		2089-2090		2090-2091		2091-2092		2092-2093		2093-2094		2094-2095		2095-2096		2096-2097		2097-2098		2098-2099		2099-2100		2100-2101		2101-2102		2102-2103		2103-2104		2104-2105		2105-2106		2106-2107		2107-2108		2108-2109		2109-2110		2110-2111		2111-2112		2112-2113		2113-2114		2114-2115		2115-2116		2116-2117		2117-2118		2118-2119		2119-2120		2120-2121		2121-2122		2122-2123		2123-2124		2124-2125		2125-2126		2126-2127		2127-2128		2128-2129		2129-2130		2130-2131		2131-2132		2132-2133		2133-2134		2134-2135		2135-2136		2136-2137		2137-2138		2138-2139		2139-2140		2140-2141		2141-2142		2142-2143		2143-2144		2144-2145		2145-2146		2146-2147		2147-2148		2148-2149		2149-2150		2150-2151		2151-2152		2152-2153		2153-2154		2154-2155		2155-2156		2156-2157		2157-2158		2158-2159		2159-2160		2160-2161		2161-2162		2162-2163		2163-2164		2164-2165		2165-2166		2166-2167		2167-2168		2168-2169		2169-2170		2170-2171		2171-2172		2172-2173		2173-2174		2174-2175		2175-2176		2176-2177		2177-2178		2178-2179		2179-2180		2180-2181		2181-2182		2182-2183		2183-2184		2184-2185		2185-2186		2186-2187		2187-2188		2188-2189		2189-2190		2190-2191		2191-2192		2192-2193		2193-2194		2194-2195		2195-2196		2196-2197		2197-2198		2198-2199		2199-2200		2200-2201		2201-2202		2202-2203		2203-2204		2204-2205		2205-2206		2206-2207		2207-2208		2208-2209		2209-2210		2210-2211		2211-2212		2212-2213		2213-2214		2214-2215		2215-2216		2216-2217		2217-2218		2218-2219		2219-2220		2220-2221		2221-2222		2222-2223		2223-2224	
-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--	-----------	--

What is claimed is:

- Claim 1. An apparatus for the printing of functional toners on a flat glass plate, said apparatus comprising:
- a. an electrostatic printing plate (10) including a polymer layer (52) bonded to an electrically conducting substrate (54) that is electrically grounded;
 - b. a first corona unit means (12) for electrically charging said electrostatic printing plate with ions from a corona discharge thereby sensitizing it and defining charged and uncharged areas;
 - c. a liquid development unit (16) which is electrically biased to deposit functional toner particles (50) on said uncharged areas of said electrostatic printing plate;
 - d. a transfer station (48) in which said flat glass plate (26) is moved into close proximity to said electrostatic printing plate (10), but not touching;
 - e. means (25) for filing the mechanical gap between said electrostatic printing plate and said glass plate with a clear toner diluent (44); and,
 - f. a second corona unit means (30) located near said glass plate (26) but away from said electrostatic printing plate (10) and which is electrically connected to a high voltage power supply (31) for creating a corona discharge which sprays free charges on said glass plate (26) and which creates an electrical field (23) that causes said toner particles (48) to transfer across the fluid filled gap (42) in an orderly manner.
- Claim 2. The apparatus of claim 1 further comprising;
- g. mechanical adjustment capability means located on said transferred corona unit including mechanical shutters (32) for controlling the exact position where toner migration from said printing plate (10) to said glass plate (26) occurs;
 - h. cleaning unit means (36) for removing residual toner particles from said printing plate (10);

- i. a drying station (27) where warm air is provided to dry said glass plate after imaging; and,
- j. support means (28) for supporting said glass plate (26) on it's edges so that said free charges in said glass tightly bind toner particles to the surface of said glass plate (26) after transfer.
- 5 Claim 3. The apparatus of claim 1 further comprising:
- k. positive phototool means for exposing said electrostatic printing plate to actinic radiation in order to cross-link the non-imaged elements of said printing plate (10) while the image elements are unexposed and not cross-linked.
- 10 Claim 4. The apparatus of Claim 1 wherein said discharge areas of said printing plate (10) develop said toner particles.
- Claim 5. The apparatus of Claim 4 wherein the polarity of said corona ions is identical to that of the toner particles in the liquid toner (50).
- 15 Claim 6. The apparatus of Claim 1 wherein said developer unit (16) includes an electrode (18, 22) which is electrically biased to a value approximately equal to the charged voltage of said printing plate (11).
- Claim 7. The apparatus of Claim 1 wherein said receiving glass plate (26) is dried of excess liquid (46) by air (27) at substantially room temperature which is blown thereover to partially fix said toner.
- 20 Claim 8. The apparatus of Claim 1 wherein said toner comprises at least three functional particle toners.
- Claim 9. A method for producing charged areas on an electrostatic printing plate which is to be developed with toner particles, by the steps of:
- 25 a. exposing said plate with a negative photo tool;
- b. using corona discharge (56) to generate ions of the opposite polarity to the toner (50); and,
- c. biasing the developer unit electrode to approximately 100 volts more than the image plate (11) voltage, in the background areas.
- 30 Claim 10. An apparatus (134) for the printing of functional toners on a flat glass plate, said apparatus comprising:

09786030-022804

- a. a flat electrostatic printing plate (102, 134) including a polymer layer (52) bonded to an electrically conducting substrate (54) that is electrically grounded;
- b. a first corona unit means (114) for electrically charge said flat electrostatic printing plate (102) with ions (110) from a corona discharge thereby sensitizing it and defining charged and uncharged areas;
- c. a liquid development unit (112) which is electrically biased to deposit functional toner particles on said uncharged areas of said flat electrostatic printing plate (102);
- d. a reverse roller unit (120) means for mechanically removing excess diluent liquid from the developed plate (102);
- e. a depress corona (122) to compact the toner particle pile before transfer;
- f. a transfer station (124) in which said flat electrostatic printing plate (102) is moved in close proximity to a flat receiving glass substrate (124);
- g. means (126) for filling the mechanical gap between flat printing plate (102) and flat receiving glass (124) with clear toner diluent (126); and,
- h. a second corona unit means (128) located near said glass plate (124) but away from said electrostatic plating plate (102) which is electrically connected to a high voltage power supply for creating a corona discharge which sprays free charges on said glass plate (124) and which creates an electrical field that causes said toner particles to transfer across the fluid filled gap in an orderly manner.

Claim 11. The apparatus of Claim 10 further comprising;

- i. electronic control mean (130) for providing adjustable time delays between each step of the process to achieve optimum image quality; and,
- j. means more resistive than the glass (124) for supporting said glass plate (124) on its edges (132) so that said free charges in said glass (124)

tightly bind toner particles on the surface of said glass plate after transfer, without distortion due to edge charge leakage.

Claim 12. The apparatus of claim 10 wherein the diluent fluid filling the gap (42) has an electrical conductivity from 0.15 to 100 pico siemens per centimeter.

Claim 13. The apparatus of Claim 10 wherein said printing plate (102) comprises a reimagable photoreceptor plate (134, 102), comprising an amorphous selenium layer, which is sensitized by a corona discharge (110) and imaged by an optical means, such as a scanned laser beam (111).

Claim 14. The apparatus of Claim 10 wherein a glass particle toner (203) is transferred to said glass plate (200) and the toner image (203) is dried with warm air to partially set the resin coating the glass particles and wherein successive layers of toner (203) build up a structure of a predetermined height.

Claim 15. The apparatus of Claim 10, wherein a palladium catalytic toner (224) is imaged on a relieved, or ribbed, glass panel (200) and subsequently plated with a metal to generate an electrode structure (204).

Claim 16. The apparatus of Claim 10 wherein a phosphor particle toner (230) is printed in a manner to coat a relieved structure (230) with a ribbed glass panel (200) having electrode lines (204) between said ribs (202).

Claim 17. An apparatus for the production of color for the black matrices on a flat plate (301) of said apparatus comprising:

- a. a color filter plate (301) with an electrical conductive coating (302) and color mosaic pattern (304), which coating (302) is electrically grounded;
- b. a corona unit (308) to charge the mosaic pattern (304) with charges (310); and,
- c. liquid toner (312) which develops in the uncharged areas of plate (301), the regions between the color mosaics (304),

wherein the polarity of the toner particles (312) is identical to the polarity of the corona generated charges (310).

Claim 18. The apparatus of Claim 17 further comprising:

- d. means (314) for drying and reflowing the toner image (312) on said coated glass plates (301);
- e. means (306) for electrically grounding the conductive layer under said toner image; and,
- 5 f. means (308) for corona charging said toner image (312);

wherein said liquid developer unit deposits black toner particles in said uncharged areas or the bare regions of said plate between said color mosaics (304).

Claim 19. The apparatus of Claim 17 wherein said glass coating (302) is 0.5μ to 25μ thick.

10 Claim 20. The apparatus of Claim 17 wherein said glass coating (302) yields a resistivity of 1 ohms per square to 10^{10} ohms per square.

Claim 21. The apparatus of Claim 17 wherein said glass coating (302) is preferably in the range of 10^1 to 10^8 ohms per square.

Claim 22. An apparatus for the production of phosphor patterned glass plates comprising:

- 15 a. a glass plate (330) patterned with a metallic, conductive materials (332, 334) on its inside surface to conduct electronic charges to ground;
- b. means to rest said plate (301) on an electrically grounded plate (336), with the conductive patterns (332, 334) facing in an outward direction;
- 20 c. means (338) for conducting said patterned conductive surface (332, 334) to a high voltage power supply (338) thereby generating an intense electric field between the patterned surface (332, 334) and said grounded plate (336);
- d. means (341) for bringing liquid toner in contact with said patterned surface (332, 334) thereby depositing toner particles (340) with a charge of the same polarity as the voltage connected to the patterned surface (332, 334), in areas adjacent to said patterned surface (332, 334), but not on it;
- 25 e. means (342) for drying said liquid toner image; and ,
- 30 f. means (344) for reflowing said toner (340) by means of heat.




Fig. 1




Fig. 2

Fig. 3A
EXPOSE




Fig. 3B
CHARGING




Fig. 3C
DELAY









Fig. 3D
LIQUID TONER
DEVELOPMENT



4/15



5/15




Fig. 5A




Fig. 5B




Fig. 6A




Fig. 6B




Fig. 6C





Fig. 6D

7/15


I plate



V plate

Fig. 7A

I plate



V plate

Fig. 7B

8/15

I plate

V plate

Fig. 8A

V intercept \approx
shield bias

I plate

V plate

Fig. 8B

V intercept \approx
grid bias




Fig. 9




Fig. 10A




Fig. 10B




Fig. 11




Fig 12




Fig. 13A




Fig. 13B




Fig. 13C




Fig. 14A




Fig. 14B




Fig. 14C




Fig. 14D

Docket No.
2349-103US

Declaration and Power of Attorney For Patent Application

English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled
ELECTROSTATIC PRINTING OF FUNCTIONAL TONER MATERIALS FOR ELECTRONIC MANUFACTURING APPLICATIONS

the specification of which

(check one)

☐ is attached hereto.

☒ was filed on October 12, 1999 as United States Application No. or PCT International Application Number PCT US99/23612 and was amended on _____

(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Priority Not Claimed

(Number)

(Country)

(Day/Month/Year Filed)

☐

(Number)

(Country)

(Day/Month/Year Filed)

☐

(Number)

(Country)

(Day/Month/Year Filed)

☐

60/104/079	October 13, 1998
(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)
(Application Serial No.)	(Filing Date)

(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status) (patented, pending, abandoned)

Form PTO-SB-01 (6-95) (Modified)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. (list name and registration number)

Richard C. Woodbridge, 26423

Stuart H. Nissim, 33,541

Send Correspondence to: Richard C. Woodbridge
Woodbridge & Associates, P.C.
P.O. Box 592
Princeton, NJ 08542-0592

Direct Telephone Calls to: (name and telephone number)
Richard C. Woodbridge 609-924-3773

Full name of sole or first inventor
Robert H. Detig

Sole or first inventor's signature

Date

Residence

185 Union Avenue, New Providence, New Jersey 07974

USX

Citizenship

United States

Post Office Address

185 Union Avenue, New Providence, New Jersey 07974

Marilyn Van Gieson

Marilyn Van Gieson
Notary Public of New Jersey
Commission Expires 7/2/04

Full name of second inventor, if any

Second inventor's signature

Date

Residence

Citizenship

Post Office Address